Durable Goods and Equipment Labeling

Flexible White Vinyl - Sheet Form

End Use Applications:

Compliance Labels Warning & Instructional Labels Nameplates Brand Identity Labels

For Durable Goods including: Outdoor Power Equipment Power Tools Appliances Electronics Recreational Vehicles Sporting Equipment Industrial Equipment...and more

For Transportation including: Automotive Aerospace Heavy Equipment

For more information on FLEXcon's pressure-sensitive film solutions for Durable Goods and Equipment Labeling, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX000308



Product:

Benefits:

- 3.5 mil flexible white vinyl provides good surface smoothness and conformability
- Print-receptive surface is compatible with most conventional and UV ink systems (we recommend evaluating the intended ribbon and ink system for compatibility with the product under the application conditions)
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass

FLEXcon® DPM® FWS

- Backed with a 90 lb. moisture stable polycoated layflat release liner ideal for sheet-form converting
- UL recognized under UL 969 UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component
- CSA accepted under CSA File No. 99214

FLEXcon[®] DPM[®] FWS

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film Adhesive Liner	3.5 (89) +/- 10% 1.0-1.1 (25-28) +/- 0.1 (3) 6.9 (175) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
Dimensional Stability (%)	MD TD	0.75 0.75	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from Acrylic Glass Polypropylene Stainless Steel	Average Oz/In 69 64 24 101	(N/m) (759) (704) (264) (1111)	ASTM D 903 (Modified for 72 hour dwell time)
Expected Shear	45		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	15		
Tack (gm/sq cm)	750 Five ware based on 2000 by: Yanan Are testing		ASTM D 2979
Expected Exterior Life	Five years based on 2000 hrs Xenon Arc testing		
Service Temperature Range	-40°F to 176°F (-40°C to 80°C) 50°F (10°C)		
Minimum Application Temperature Storage Stability	One year when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contemplated use. Last Modified On: 08/15/2019



FLEXCON 1 FLEXcon Industrial Park, Spencer, MA 01562-2642, Telephone (508) 885-8300 FAX (508) 885-8301 www.FLEXcon.com